



// ONE BRAND // ONE SOURCE // ONE SYSTEM

Product sheet

## Intermediate rubber, uncured

### Technical properties

Colour		Black
Rubber	DIN ISO 1629	NR
Hardness	DIN ISO 7619-1	65 Shore A
Abrasion	DIN ISO 4649	mm <sup>3</sup>
Density	DIN EN ISO 1183-1	1,2 g/cm <sup>3</sup>
Tensile Strength	DIN 53 504	19 N/mm <sup>2</sup>
Elongation at break	DIN 53 504	510 %
Resilience	DIN 53 512	%
Tear Growth Resistance	ISO 34-1 Methode A	18 N/mm

The information given above is based on random test results during production and represent the average result of our products as given from a statistic long-term evaluation. We reserve the right for changes to technical specifications without prior notice, provided they ensure technical improvement without major modifications of the product. Colored rubber products containing the polymer NR, can change their color due to the natural color deviation of natural rubber.